

|                                                                                                                                           |                                                                                                                                           |                                                                                                               |                                                                                                                               |                       |                                          |
|-------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------|-----------------------|------------------------------------------|
| Colores<br>Colours                                                                                                                        |                                                                                                                                           | Medida nominal (cm)<br>Nominal size                                                                           | Espesor - E (mm)<br>Thickness - E                                                                                             | Tipología<br>Typology | Deslizamiento<br>Coefficient of friction |
| <br>White                                                |                                                                                                                                           | 31,6x100 <sup>R</sup>                                                                                         | 9,7                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 31,6x100 <sup>R</sup> Duna                                                                                    | 10,4                                                                                                                          | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 29,5x90 <sup>R</sup>                                                                                          | 9,3                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 29,5x59,5 <sup>R</sup>                                                                                        | 9,1                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 30,5x60,5                                                                                                     | 9,1                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 25x75                                                                                                         | 9,7                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 39,6x119,2 <sup>R</sup>                                                                                       | 6,5                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           | 39,6x119,2 <sup>R</sup> Kube                                                                                  | 8,5                                                                                                                           | BIII - GL             | —                                        |
|                                                                                                                                           |                                                                                                                                           |                                                                                                               |                                                                                                                               |                       |                                          |
|  Variación cromática uniforme<br>Uniform Colour Variation |  Variación gráfica uniforme<br>Uniform Graphic Variation |                                                                                                               |                                                                                                                               |                       |                                          |
|  Porcelánico<br>Porcelain                                 |  Pavimento<br>Floor tiles                                |  Revestimiento<br>Wall tiles |  Resistencia a la helada<br>Frost resistance |                       |                                          |

| CARACTERÍSTICAS TÉCNICAS<br>TECHNICAL FEATURES                                                                                                                                                              |  |                                                        |                                                                                                                                                                                                                                                                                                                                                     |                                                                                                                                                                              |                                                                                          |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|--------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------|
|                                                                                                                                                                                                             |  | ISO 13006<br>UNE-EN 14411                              | Bla     | BIIb   | BIII  |
|  Longitud y anchura<br>Length and width                                                                                     |  | EN ISO 10545-2                                         | ± 0,6 % ± 2,0 mm                                                                                                                                                                                                                                                                                                                                    | ± 0,6 % ± 2,0 mm                                                                                                                                                             | ± 0,5 % ± 2,0 mm                                                                         |
|  Espesor<br>Thickness                                                                                                       |  | EN ISO 10545-2                                         | ± 5 % ± 0,5 mm                                                                                                                                                                                                                                                                                                                                      | ± 5 % ± 0,5 mm                                                                                                                                                               | ± 10 % ± 0,5 mm                                                                          |
|  Rectitud de lados<br>Straightness of sides                                                                                |  | EN ISO 10545-2                                         | ± 0,5 % ± 1,5 mm                                                                                                                                                                                                                                                                                                                                    | ± 0,5 % ± 1,5 mm                                                                                                                                                             | ± 0,5 %                                                                                  |
|  Ortogonalidad<br>Rectangularity                                                                                          |  | EN ISO 10545-2                                         | ± 0,5 % ± 2,0 mm                                                                                                                                                                                                                                                                                                                                    | ± 0,5 % ± 2,0 mm                                                                                                                                                             | ± 0,3 % ± 1,5 mm                                                                         |
|  Planitud de superficie<br>Surface flatness                                                                               |  | EN ISO 10545-2                                         | ± 0,5 % ± 2,0 mm                                                                                                                                                                                                                                                                                                                                    | ± 0,5 % ± 2,0 mm                                                                                                                                                             | + 0,5 % ; - 0,3 %<br>+ 2 mm ; - 1,5 mm                                                   |
|  Absorción de agua<br>Water absorption                                                                                    |  | EN ISO 10545-3                                         | E ≤ 0,5 %<br>Max. Individual 0,6%                                                                                                                                                                                                                                                                                                                   | 0,5 % ≤ E ≤ 3 %                                                                                                                                                              | E > 10 %                                                                                 |
|  Fuerza de rotura (N)*<br>Breaking strength*                                                                              |  | EN ISO 10545-4                                         | E > 7,5 mm > 1300 N<br>E < 7,5 mm > 700 N                                                                                                                                                                                                                                                                                                           | E > 7,5 mm > 1100 N<br>E < 7,5 mm > 700 N                                                                                                                                    | E > 7,5 mm > 600 N<br>E < 7,5 mm > 200 N                                                 |
|  Resistencia a la flexión (N/mm²)<br>Modulus of rupture                                                                   |  | EN ISO 10545-4                                         | > 35 N/mm²<br>Min. Individual 35 N/mm²                                                                                                                                                                                                                                                                                                              | > 35 N/mm²<br>Min. Individual 27 N/mm²                                                                                                                                       | E > 7,5 > 12 N/mm²<br>E < 7,5 > 15 N/mm²                                                 |
|  Resistencia a la abrasión profunda (Solo UGL)<br>Surface deep abrasion resistance (Only UGL)                             |  | EN ISO 10545-6                                         | Mín. 175 mm³                                                                                                                                                                                                                                                                                                                                        | Mín. 175 mm³                                                                                                                                                                 | No aplica<br>Not apply                                                                   |
|  Resistencia a la abrasión superficial (Solo GL)<br>Surface abrasion resistance (Only GL)                                 |  | EN ISO 10545-7                                         | Valor declarado<br>Declared value                                                                                                                                                                                                                                                                                                                   | Valor declarado<br>Declared value                                                                                                                                            | No aplica<br>Not apply                                                                   |
|  Coeficiente de dilatación térmica lineal (1/k)<br>Coefficient of linear thermal expansion                                |  | EN ISO 10545-8                                         | Valor declarado<br>Declared value                                                                                                                                                                                                                                                                                                                   | Valor declarado<br>Declared value                                                                                                                                            | Valor declarado<br>Declared value                                                        |
|  Resistencia al choque térmico<br>Thermal shock resistance                                                                |  | EN ISO 10545-9                                         | Resiste<br>Resist                                                                                                                                                                                                                                                                                                                                   | Resiste<br>Resist                                                                                                                                                            | Resiste<br>Resist                                                                        |
|  Resistencia al cuarteo<br>Crazing resistance                                                                             |  | EN ISO 10545-11                                        | Resiste<br>Resist                                                                                                                                                                                                                                                                                                                                   | Resiste<br>Resist                                                                                                                                                            | Resiste<br>Resist                                                                        |
|  Resistencia a la helada<br>Frost resistance                                                                              |  | EN ISO 10545-12                                        | Resiste<br>Resist                                                                                                                                                                                                                                                                                                                                   | No resiste<br>Not resist                                                                                                                                                     | No resiste<br>Not resist                                                                 |
|  Deslizamiento<br>Coefficient of friction                                                                                 |  | UNE ENV 41901<br>DIN 51130<br>DIN 51097<br>ANSI A137.1 | Valor declarado<br>Declared value                                                                                                                                                                                                                                                                                                                   | Valor declarado<br>Declared value                                                                                                                                            | No aplica<br>Not apply                                                                   |
|  Resistencia a productos de limpieza y aditivos para piscina<br>Resistance to household chemicals and swimming pool salts |  | EN ISO 10545-4                                         | Min GB                                                                                                                                                                                                                                                                                                                                              | Min GB                                                                                                                                                                       | Min GB                                                                                   |
|  Resistencia a bajas concentraciones<br>Resistance to low concentrations                                                  |  | EN ISO 10545-13                                        | GLA-ULA / GLB (Ecco, Nawan)                                                                                                                                                                                                                                                                                                                         | GLA                                                                                                                                                                          | GLA                                                                                      |
|  Resistencia a altas concentraciones<br>Resistance to high concentrations                                                 |  | EN ISO 10545-13                                        | GHA-UHA / GHB (Ecco, Nawan)                                                                                                                                                                                                                                                                                                                         | GHA                                                                                                                                                                          | GHA                                                                                      |
|  Resistencia a las manchas<br>Resistance to stains                                                                        |  | EN ISO 10545-14                                        | > 3                                                                                                                                                                                                                                                                                                                                                 | > 3                                                                                                                                                                          | > 3                                                                                      |

Las características indicadas son generales por grupo de absorción, para características concretas de modelo y color solicitar la ficha técnica correspondiente. The characteristics indicated are general for each absorption group, for specific characteristics of the model and color, please request the corresponding technical data sheet.

\* E corresponde al espesor indicado en la tabla de la esquina superior derecha. E is the thickness shown in the upper right-hand corner of table.